

丸 棒



酸洗



引抜

■丸棒 SUS304・304L・310S・316・316L <ピーリング、酸洗、引抜、ミガキ、センタレス>

鋼種	304					304L					310S					316					316L					
	ピーリング	酸洗	引抜	ミガキ	センタレス	ピーリング	酸洗	引抜	ミガキ	センタレス	ピーリング	酸洗	引抜	ミガキ	センタレス	ピーリング	酸洗	引抜	ミガキ	センタレス	ピーリング	酸洗	引抜	ミガキ	センタレス	
2			●	●	●														●							
2.5			●	●																						
3			●	●	●									●					●	●						
3.5				●	●																					
4			●	●	●									●					●	●					●	
4.5				●																						
5			●	●	●									●					●	●					●	
5.5		●		●																						
6		●	●	●	●							●		●			●		●	●		●		●		●
6.5				●																						
7		●	●	●	●									●					●	●					●	
8		●	●	●	●		●					●		●			●		●	●		●		●		●
9		●	●	●	●		●					●		●			●		●	●		●		●		●
10		●	●	●	●		●					●		●			●		●	●		●		●		●
11			●	●	●									●					●	●						
12		●	●	●	●							●					●		●	●		●		●		●
13		●	●	●	●		●					●					●		●	●		●				
14		●	●	●	●							●					●		●	●						
15		●	●	●	●														●	●					●	
16	●	●	●	●	●	●					●	●				●	●		●	●	●	●	●	●	●	●
17	●		●	●	●											●			●	●					●	
18	●		●	●	●						●					●			●	●		●			●	
19	●	●	●	●	●	●					●					●			●	●	●	●	●	●	●	●
20	●	●	●	●	●	●					●					●			●	●	●	●	●	●	●	●
22	●		●	●	●	●					●					●			●		●		●		●	
24	●			●												●										
25	●		●	●	●	●					●					●			●	●		●			●	
26	●			●												●			●							
28	●		●	●	●						●					●			●		●					
30	●		●	●	●	●					●					●			●	●	●	●	●	●	●	●
32	●		●	●	●	●					●					●			●		●		●			
34	●			●												●										
35	●		●	●	●	●					●					●			●	●	●	●	●	●	●	●
36	●										●					●					●					
38	●			●	●	●					●					●			●		●					

●...ピーリング ●...酸洗 ●...引抜 ●...ミガキ ●...センタレス

丸 棒

丸棒 SUS304・304L・310S・316・316L <ピーリング、酸洗、引拔、ミガキ、センタレス>

外径	304					304L					310S					316					316L				
	ピーリング	酸洗	引拔	ミガキ	センタレス	ピーリング	酸洗	引拔	ミガキ	センタレス	ピーリング	酸洗	引拔	ミガキ	センタレス	ピーリング	酸洗	引拔	ミガキ	センタレス	ピーリング	酸洗	引拔	ミガキ	センタレス
250	●					●					●					●					●				
260	●															●					●				
270	●															●					●				
280	●															●					●				
290	●															●					●				
300	●															●					●				
310	●															●					●				
320	●															●					●				
330	●															●					●				
340	●															●					●				
350	●															●					●				
360	●															●					●				
370	●															●					●				
380	●																								
390	●																								
400	●															●					●				
420	●															●					●				
450	●															●					●				
480	●																								
500	●															●					●				

※その他材質も取り扱いございます。詳しくは営業担当までお問い合わせ下さい。 ●…ピーリング ●…酸洗 ●…引拔 ●…ミガキ ●…センタレス

重量計算式

1m当りの重量(W:mg/m)の数値は次の計算式によって計算し、JIS Z 8401により有効3桁に丸める。

$$W = \text{係数} \times \text{半径mm} \times \text{半径mm} \times 3.14159(\pi)$$

係数	SUS304, 304L	0.00793
	SUS316, 316L, 310S, 309S	0.00798
	SUS430	0.00770
	SUS403	0.00775

注:切断品の場合、切りしろが重量に加算されることがあります。

外径公差基準表 (JIS G 4318)

引拔・ミガキ丸棒 (h-9) 単位:mm

3以下	+0 -0.025
3を超え 6以下	+0 -0.03
6を超え 10以下	+0 -0.036
10を超え 18以下	+0 -0.043
18を超え 30以下	+0 -0.052
30を超え 50以下	+0 -0.062
50を超え 80以下	+0 -0.074
80を超え 120以下	+0 -0.087

センタレス丸棒 (h-7) 単位:mm

3以下	+0 -0.01
3を超え 6以下	+0 -0.012
6を超え 10以下	+0 -0.015
10を超え 18以下	+0 -0.018
18を超え 30以下	+0 -0.021
30を超え 50以下	+0 -0.025