

銅板



銅板 主要サイズ別重量表

参考重量 単位:kg/ 枚

銅種 寸法 板厚(mm)	SUS304		SUS304L		SUS430				SUS316	SUS316L	SUS310S	
	1000×2000	1219×2438 (4f×8f)	1524×3048 (5f×10f)	2000×4000	1000×2000 (4f×8f)	1219×2438 (4f×8f)	1524×3048 (5f×10f)	2000×4000	1000×2000	1219×2438 (4f×8f)	1524×3048 (5f×10f)	2000×4000
0.3	4.76	7.07			4.62				4.79	7.11		
0.4	6.34	9.43			6.16				6.38	9.49		
0.5	7.93	11.8			7.70				7.98	11.9		
0.6	9.52	14.1			9.24				9.58	14.2		
0.7	11.1	16.5			10.8				11.2	16.6		
0.8	12.7	18.9			12.3	18.3			12.8	19.0		
1	15.9	23.6			15.4	22.9			16.0	23.7		
1.2	19.0	28.3			18.5	27.5			19.2	28.5		
1.5	23.8	35.4	55.3		23.1	34.3			23.9	35.6	55.6	
2	31.7	47.1	73.7		30.8	45.8			31.9	47.4	74.1	
2.5	39.6	58.9	92.1		38.5	57.2			39.9	59.3	92.7	
3	47.6	70.7	111		46.2	68.6			47.9	71.1	111	
4	63.4	94.3	147	254	61.6	91.5			63.8	94.9	148	
4.5	71.4	106	166									
5	79.3	118	184	317	77.0	114			79.8	119	185	
6	95.2	141	221	381	92.4	137			95.8	142	222	383
7	111	165	258		108	160			112	166	259	447
8	127	189	295	508	123	183	286		128	190	297	511
9	143	212	332	571	139	206	322		144	213	334	575
10	159	236	368	634	154	229	358		160	237	371	638
12	190	283	442	761	185	275	429	739	192	285	445	766
14	222	330	516	888	216	320	501		223	332	519	894
15	238	354	553	952	231	343			239	356	556	958
16	254	377	589	1015	246	366	572		255	380	593	1022
18	285	424	663	1142	277	412	644	1109	287	427	667	1149
19	301	448	700	1206	293	435	680		303	450	704	1213
20	317	471	737	1269	308	458	715		319	474	741	1277
22	349		811	1396			787				816	1405
25	396		921	1586							927	1596
28			1031	1776							1038	1788
30			1105	1903				1848			1112	1915
32			1179	2030							1186	2043
35			1289	2221								2234
38			1400	2410							1297	2426
40			1473	2538							1483	2554
45			1657	2854								2873
50			1842	3172								3192
55			2026	3490								3511
60			2210	3806							2224	3830
65			2394	4123								4150
70				4441								4469
75				4758								4788
80				5075								5107
85				5392								5426
90				5710								5746
95				6027								
100				6344								6384

銅板

銅板 仕様別(板厚・仕上・材質)取り扱い表

		材質												
板厚(mm)	仕上	303	304	304L	309S	310S	316	316L	317L	321	410	410S	430	329J4L
0.3	2B		●					●					●	
0.4	2B		●	●				●					●	
0.5	2B		●	●		●	●	●					●	
0.6	2B		●	●			●	●					●	
0.7	2B		●											
0.8	2B		●	●		●	●	●					●	
1	2B		●	●	●	●	●	●					●	
1.2	2B		●	●	●	●	●	●					●	
1.5	2B		●	●	●	●	●	●	●	●		●	●	
2	2B		●	●	●	●	●	●	●	●		●	●	●
2.5	2B		●	●			●	●					●	
3	2B		●	●	●	●	●	●	●	●		●	●	
4	2B		●	●			●	●					●	
5	2B		●				●	●						
6	2B		●	●			●	●						
2	NO,1		●											
3	NO,1		●	●	●	●	●	●	●					●
4	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
4.5	NO,1		●											
5	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
6	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
7	NO,1		●				●	●						
8	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
9	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
10	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
12	NO,1	●	●	●	●	●	●	●	●	●	●		●	●
14	NO,1	●	●	●		●	●	●			●		●	
15	NO,1	●	●	●	●	●	●	●		●				
16	NO,1	●	●	●	●	●	●	●	●	●	●		●	
18	NO,1	●	●	●	●	●	●	●			●		●	
19	NO,1	●	●	●	●	●	●	●		●	●		●	
20	NO,1	●	●	●	●	●	●	●		●	●		●	
22	NO,1	●	●	●	●	●	●	●		●	●		●	
25	NO,1	●	●	●	●	●	●	●		●	●		●	
28	NO,1	●	●	●		●	●	●						
30	NO,1	●	●	●	●	●	●	●		●	●		●	
32	NO,1	●	●	●		●	●	●						
35	NO,1	●	●	●	●	●	●	●			●			
38	NO,1	●	●	●			●	●						
40	NO,1	●	●	●	●	●	●	●		●	●		●	
45	NO,1	●	●	●	●	●	●	●			●			
50	NO,1	●	●	●	●	●	●	●		●	●		●	
55	NO,1	●	●				●	●						
60	NO,1	●	●	●		●	●	●						
65	NO,1	●	●				●	●						
70	NO,1	●	●	●			●	●						
75	NO,1		●				●	●						
80	NO,1	●	●				●	●						
85	NO,1		●				●	●						
90	NO,1		●				●	●						
95	NO,1		●											
100	NO,1		●				●	●						